



### NEUTRAL 440 C

Neutral 440 C films are highly effective at reducing solar heat gain, whilst at the same time continuing to allow some natural light transmission. They help noticeably reduce solar glare, their tinted aspect helping convey a touch of colour and customization to the external aspect of a building. Designed to act as a security film, it provides protection by holding shattered glass in place in the event of an impact.



## TECHNICAL DATASHEET

Data calculated based on film applied to clear glass 3 mm thick (\*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	63 %
Reflection of external visible light	11 %
Reflection of internal visible light	10 %
Total solar energy rejected	37 %
Total solar energy rejected 2*	34 %
Solar ratio :	
Solar energy reflection	7 %
Solar energy absorption	30 %
Solar energy transmission	63 %
Reduction in Solar Glare	43 %
g-value	0.66
u-value	5.8
Shading coefficient	0.7
Installation type : Internal application	
Roll length	30,5 m
PET / PVC composition	PET
Thickness	125 μ
Colour : NEUTRAL	

### **CONSTRUCTION**

- 1. "Hard" scratch resistant layer, for durability and ease of
- maintenance during window cleaning **2.** High optical quality polyester
- **3.** Bonding adhesive
- 4. High optical quality polyester
- 5. Reinforced PS Adhesive to accompany the elasticity of the film
- in case of impact, glass polymerization within 30 days
- 6. Protection release liner, disposable after installation

#### MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. sun pose 0808 or 0805 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data, SOLAR SCREEN® reserves the right to modify the composition of its films at any time.

SOLAR SCREEN® EUROPEAN SALES CENTER 204 ROUTE D'ARLON L-8010 STRASSEN TEL : +352 26 00 84 82 WWW.SOLARSCREEN.EU

# INSTALLATION ADVICE

Vertical installation and on standard glass surface\*\*

	Clear single pane	$\checkmark$	
	Tinted single pane	1	
	Reflective tinted single pane	$\checkmark$	
	Clear double pane	$\checkmark$	
	Tinted double pane	1	
	Reflective tinted double pane	$\checkmark$	
	Gas-filled double pane - Low E	1	
	STADIP EXT. clear double pane	1	
	STADIP INT. clear double pane	×	

Yes Caution XNot recommended

\*Recommendations provided on the basis of a glazed surface covering up to 2.5m<sup>2</sup>, contact us for definitive details or to obtain a thermal chock analysis report.

